

PCT

A61F 13/08.

English

English

(10) International Publication Number WO 01/80798 A1

## (43) International Publication Date 1 November 2001 (01.11.2001)

- (51) International Patent Classification7: 13/02
- (21) International Application Number: PCT/GB01/01825
- (22) International Filing Date: 24 April 2001 (24.04.2001)
- (25) Filing Language:
- (26) Publication Language:
- (30) Priority Data: 0009805.3
- 25 April 2000 (25.04.2000) GB
- (71) Applicant (for all designated States except US): BSN MEDICAL LTD. [GB/GB]; Brierfield Mills, Brierfield, Nelson, Lancashire BB9 5NJ (GB).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): EVANS, John, Christopher [GB/GB]; 14 Haugh Fold, Newhey, Lancashire OL16 3RF (GB). CLAPHAM, Keith [GB/GB]; 110 Hallam Road, Nelson, Lancashire BB9 8DJ (GB).


- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW,
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

#### Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: BANDAGE



(57) Abstract: A bandage comprising a weft insertion fabric, in particular a light compression bandage which is a non-laminated and/or single layer bandage comprising a west insertion fabric or a conformable bandage that essentially consists of a weft insertion fabric, and a method of treating venous leg, lymphodoema, muscle strain or muscle sprain, which comprises applying such a bandage.

WO 01/80798 A

WO 01/80798

### BANDAGE

The present invention relates to stretch fabrics and bandages, and in particular to light compression bandages.

5

10

Stretch fabrics are often used in the manufacture of bandages to provide bandages with the properties of light support and low compression. Such bandages are often used in the treatment of sprains, strains and venous leg ulcers. The bandages may also be used in sport applications where support is required on a body limb. These bandages should have sufficient elasticity, or stretch, to enable them to conform to the bandaged area and when secured, to allow limited movement and swelling to take place so that the circulation is not adversely affected.

15

20

25

30

Typical light compression bandages include elastic adhesive bandages (EAB), which traditionally comprise natural yarns, woven to form the fabric. Normally the yarns are woven using a plain weave design. In the manufacturing field of light compression bandages, the simplicity of woven fabrics is preferred over that of knitted fabrics. The woven fabrics of the prior art EABs offer extension in the warp, or length, direction only. Traditionally natural fibre materials were used as these materials were seen as superior to synthetic materials. Although synthetic and/or elastomeric yarns may offer greater initial stretch and superior fatigue resistance than natural yarns, such as cotton, natural yarns have been traditionally preferred for EABs. This is due to the aesthetic appearance of natural yarns and the perceived greater control stretch value, or controlled compression, of natural yarns than synthetic and/or elastomeric yarns.

However, regardless of what types of yarns are used to produce a stretch fabric, the loss of fatigue resistance over-time still

remains a problem. In particular, the loss of fatique resistance remains a problem to the previously known light compression bandages, e.g. EABs, which can suffer from loss of fatigue resistance within a few hours of application.

5

It is an object of the present invention to provide a light compression bandage, which addresses the problems of the prior art light compression bandages.

10

It is an object of the present invention to provide a light compression bandage, which offers greater conformability than the prior art light compression bandages.

15

It is a further object of the present invention to provide a light compression bandage, which has greater fatigue resistance than the prior art light compression bandages.

Accordingly, there is provided a bandage comprising a weft insertion fabric.

20

We also provide a non-laminated and/or single layer bandage comprising a weft insertion fabric.

Further, we provide a conformable bandage that essentially 25 consists of a weft insertion fabric.

We further provide a conformable, non-laminated and/or single layer, bandage comprising a weft insertion fabric.

30

The term "weft insertion" is known in the art to mean a thread. yarn, filament or the like which is inserted in the weft direction and

10

15

25

held in place across the warp direction by pillar threads, yarns, filaments or the like.

We further provide the use of a bandage according to the invention in the treatment or alleviation of venous leg ulcers, lymphodoema, muscle strain or muscle sprain.

In particular we provide a use of a bandage according to the invention for the treatment of venous leg ulcers, lymphodoema, muscle strain or muscle sprain, which comprises applying a bandage according to the invention to an affected site on a patient.

Advantages of the present invention include the improved extension fatigue resistance of the bandage. This enables the bandages to have a longer working life thus saving time and costs as associated with the usage of traditional light compression bandages.

Another advantage of the present invention over the prior art is that the bandages of the present invention have improved conformability. This advantage may be best seen in the weft direction where the improved conformability over the prior art may be the greatest.

Previous light compression bandages, e.g. EABs, have had very little weft extension, if at all. Previously this was not seen as a problem, however surprisingly we have found that the present invention, by having some extension or stretch in the weft direction of the bandage increases conformability of the bandage. If the bandage has too much extension or stretch in the weft direction, as in a full knit fabric or bandage conformability is decreased not increased. Therefore, if a person skilled in the art wanted to

increase the stretch of the fabric of the bandage in the weft direction, they would be directed to produce a knit fabric, which may not necessarily increase conformability of the material.

5 The present invention therefore overcomes this prejudice in the art.

The present invention also makes it feasible to use other yarns besides natural yarns like cotton in the material for the bandage.

. Δ.

10

30

Any suitable yarn may be used in the invention although preferably the present invention will comprise a mixture of natural and synthetic yarns.

15 Typical staple fibre yarns suitable for use in the present invention include cellulosic fibre yarns such as cotton fibre or staple viscose rayon fibre yarns.

Suitable textured filaments for use in composite warp yarns or 20 as textured yarns alone in bandages of the invention include textured filament yarns of synthetic fibre polymers such as polyamide or polyester.

Preferred textured filament yarns for use in the invention are 25 textured filament yarns, e.g. nylon 6,6. Apt yarns of this type are known as 2/78 D Tex nylon.

The composite yarns may comprise a cotton yarn and a textured polyamide yarn; suitably the composite yarn comprises a cotton yarn and a textured yarn twisted together.

15

25

Although any suitable yarn may be used, the pillar yarns may comprise synthetic, elastomer and/or natural fibres or filaments, or any combination thereof.

5 Suitable yarns may include cellulose yarns, e.g. cotton and generic products of cotton, and/or nylon.

Aptly the pillar yarns will contain synthetic and elastomeric fibres or filaments.

Preferably the weft yarns i.e. the weft insertions, will comprise natural yarns, this may include cellulose yarns. Apt yarns for the weft yarns of the present invention may comprise cotton and generic products of cotton.

Other typical yarns suitable as weft yarns of the present invention may comprise rayon or combinations of cotton and rayon.

Bandages according to the invention may comprise one or 20 more inlay yarn for every one composite yarn.

The elastomeric yarn may comprise any natural or synthetic elastomers known <u>per se.</u> Natural elastomers include, for example, natural rubber.

Preferred synthetic elastomers include polyurethane elastomers. Such yarns may comprise 85% polyurethane. Thus, a polyurethane elastomeric yarn need not be 100% polyurethane.

30 Suitable polyurethane elastomeric yarns include those known as LYCRA (Trade Mark).

25

Other favoured polyurethane elastomeric yarns are ones, which have restricted stretching properties.

For example, preferred polyurethane elastomeric yarns are those, which are wrapped with a less elastic filament, i.e. a cotton or a synthetic wrapping.

The yarns used in the present invention, both for the pillar yarn and the weft insertion may be twisted to give further elastic properties to the yarn or to simply combine more than one yarn to form the composite yarn.

The twist level for the composite yarn can suitably be from 60 to 800 turns/meter, preferably less than 600 turns/meter and preferably more than 200 turns/metre.

Preferably, the bandage of the present invention will have an adhesive to aid holding of the bandage to the user. Clearly any adhesive used should be capable of adhering to that part of the body to which it is to be attached and to adjacent overlapping turns of the bandage.

Preferably the adhesive will be a pressure sensitive adhesive. By the term "pressure sensitive adhesive", it is intended to mean an adhesive, which is inherently tacky, visco-elastic and cohesive in its normal dry state.

The adhesive may be applied wholly or partly to one face of the bandage. However, preferably the adhesive layer should cover most of the area of one face of the bandage.

10

25

30

The adhesive, if used, may be a water permeable or water impermeable adhesives. Preferred water impermeable adhesives include natural rubber latex based adhesives, synthetic rubber based adhesives and hot-melt adhesives. Less preferred water impermeable adhesives include polyvinyl ethers and certain acrylate ester copolymers containing hydrophilic groups.

The light compression bandages of the present invention will now be illustrated, but by no way limited, by reference to the following drawings.

Figure 1 is a schematic view of the basic structure of a typical traditional woven bandage of the prior art.

15 Figure 2 is a schematic view of the basic structure of a light compression bandage of the present invention.

In Figure 1 the basic structure of a typical woven fabric bandage is shown, with warp yarns (1) and a weft yarns (2) that 20 cross back and forth across the warp direction of the bandage, and down the warp direction of the bandage at each pick.

Figure 2 shows the basic structure of the bandage of the present invention with weft inserts (4) and pillar yarns comprising a first yarn (3) and a second yarn (5).

This embodiment of the present invention therefore shows loops in the warp direction but has a straight yarn in the weft direction. The weft ends do not loop but are free, like the cut ends of woven products. Fabric or bandages of this embodiment of the present invention may therefore resemble woven products in appearance.

The present invention will now be illustrated by the following examples.

# 5 Example 1

15

A light support compression bandage of the invention was formed from a fabric produced on a Paschel/Tricot high-performance warp-knitting machine suitable for weft insertion using a cotton/elastomeric composite yarn for the pillar yarns and a cotton/rayon yarn for the weft insertions.

The composite yarns used in this example for the pillar yarns were 19.68 Tex staple fibre cotton yarn and 1/78 D Tex elastomeric yarn respectively. The composite warp yarns contain the cotton and elastomeric yarns twisted together. The yarns used for the weft insertions were 19.68 Tex fibre cotton yarn and 29.8 Tex rayon yarn.

The bandage was 10 cm wide and comprised 71 ends/10cm for the pillar yarns. This bandage when applied to a limb at approximately 30% extension caused a compressive force on the limb of 30 mmHg.

## CLAIMS

- A bandage comprising a weft insertion fabric.
- 5 2. A bandage according to claim 1, which is a non-laminated bandage.
  - A bandage according to claim 1, which is a single layer bandage.
  - A bandage according to claim 1, which essentially consists of a weft insertion fabric.
- A bandage according to claim 4, which is a non-laminated
   bandage.
  - A bandage according to claim 4, which is a single layer bandage.
- A bandage according to claim 1, which comprise a mixture of natural and synthetic yarns.
- A bandage according to claim 1, which comprises a weft insertion fabric which comprises staple cotton fibre yarns, staple viscose rayon fibre yarns, textured polyamide filament yarns, textured polyester filament yarns, textured polyamide filament composite warp yarns and/or textured polyester filament composite warp yarns.
- A bandage according to claim 1, which comprises an adhesive layer which covers most of the area of one face of the bandage.

 A method of treating verious leg ulcers, lymphodoema, muscle strain or muscle sprain, which comprises applying a bandage according to claim 1 to an affected site on a patient.




Figure 1




Figure 2

A. CLASSIFICATION OF SUBJECT MATTER IPC 7 A61F13/08 A61F13/02

According to Internetional Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols) IPC 7 A61F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUM	ENTS CONSIDERED TO BE RELEVANT	
Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevent to claim No.
х	US 4 424 808 A (JUNG HARALD ET AL) 10 January 1984 (1984-01-10) column 1, line 6 -column 4, line 13 column 7, line 65 -column 8, line 6; figures 1-3	1-9
X	US 3 523 528 A (KNOHL HERBERT ET AL) 11 August 1970 (1970-08-11) the whole document	1-9
Х	US 4 734 320 A (OHIRA OSAMU ET AL) 29 March 1988 (1988-03-29) column 1, line 53 -column 3, line 17	1-9
X	US 1 257 677 A (ROBINSON & SONS LTD) 22 December 1971 (1971-12-22) page 1, line 39 -page 2, line 118	1-9
X Furth	page 1, line 39 -page 2, line 118 -/  er documents are listed in the continuation of box C.      Patent tamby member	s are listed in annex.

* Special categories of clied documents:  *A' document defining the general state of the art which is not considered to be of particular miswance  *E' earlier document but published on or after the International Ring data  *I' document which may threw datase on priority data(p) or  *I' document which may threw datase on priority data(p) or classification of the properties of the properti	"I" later document published effor the International filing date or priority data and not in conflict with the application but or priority data and not in conflict with the application but forwards.  "O document of particular relevance; he claimed hivention cannot be considered novel or cannot be considered to involve an inventive step when the document is lation above. "I document of particular relevance; he claimed revinetion cannot be considered to involve an inventive step when the document is lation above. The construction of particular relevance; he claimed revinetion cannot be considered to involve an inventive step when the construction of particular relevance; he called the priority of the construction of the considered to involve an inventive step when the construction of the construction of the construction of the construction of the same patent family.  3" document member of the same patent family
Date of the actual completion of the international search  13 August 2001	Date of mailing of the Internetional search report 22/08/2001
Neme end mailing eddress of the ISA European Palent Office, P. B. 5818 Patentiaan 2 NL - 2280 HV Pillswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo ni, Fax: (+31-70) 340-3016	Authorizad officer Seabra, L

# INTERNATIONAL SEARCH REPORT

national Application No PCT/GB 01/01825

· ·		PCT/GB 01/01825
	INION) DOCUMENTS CONSIDERED TO BE RELEVANT	
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relavant to ctalm No.
X	GB 2 070 656 A (BRAUN FRANZ) 9 September 1981 (1981-09-09) the whole document	1-8
(	US 5 540 982 A (SCHOLZ MATTHEW T ET AL) 30 July 1996 (1996-07-30) column 1, line 10-13 column 6, line 10-43; figures 1A-1D	1-8
(	GB 2 178 764 A (SMITH & NEPHEW ASS) 18 February 1987 (1987-02-18) the whole document	1-9

_						<del></del>
	atent document d in search report		Publication date		Patent family member(s)	Publication date
US	4424808	Α	10-01-1984	DE	2656043 A	15-06-1978
				DE	2730277 A	25-01-1979
				DE	2737268 A	01-03-1979
				DE	2738933 A	15-03-1979
				ČĀ	1070217 A	22-01-1980
				DE	2660689 C	
						20-10-1983
				AT	378121 B	25-06-1985
				AT	261081 A	15-11-1984
				AT	378122 B	25-06-1985
				AT	273981 A	15-11-1984
				AT	367999 B	25-08-1982
				AT	448978 A	15-01-1982
				BE	868707 A	03-11-1978
				CH	642532 A	30-04-1984
				ES	471429 A	16-09-1979
				FR	2396543 A	02-02-1979
				GB	2010933 A,	
				NL	7807263 A.	B. 09-01-1979
				NL	9000816 A	01-08-1990
				SE	443718 B	10-03-1986
				SE	7807497 A	06-01-1979
				DE		
				VE	2760136 C	24-10-1985
US 	3523528	Α	11-08-1970	SE	357923 B	16-07-1973
US	4734320	Α	29-03-1988	JP	1687753 C	11-08-1992
				JP	3049953 B	31-07-1991
				JP	62252495 A	04-11-1987
US	1257677	Α		NONE		
GB	2070656	Α	09-09-1981	DE	3001147 A	16-07-1981
				AT	385785 B	10-05-1988
				AT	387597 B	10-02-1989
				BE	887063 A	04-05-1981
				· CH	654605 A	28-02-1986
				FR	2473568 A	17-07-1981
				NL	8100129 A,	
				SE	8100010 A	16-07-1981
US	5540982	Α	30-07-1996	US	5512354 A	30-04-1996
				US	6159877 A	12-12-2000
				ÄÜ	687789 B	05-03-1998
				AU	6231194 A	15-08-1994
				AU	718627 B	
						20-04-2000
				AU	6994598 A	27-08-1998
				CA	2152675 A	04-08-1994
				CN	1116861 A	14-02-1996
				EP	0680527 A	08-11-1995
				JP	8505909 T	25-06-1996
				МX	9400665 A	31-08-1994
				WO	9417229 A	04-08-1994
GB	2178764	Α	18-02-1987	ZA	8506603 A	28-05-1986